

**AMENDMENTS TO THE SPECIFICATION**

Please replace paragraph [0066] with the following replacement paragraph:

[0066] In the cases of the invention examples Symbols [[A-1]]B-1 to C-1 and E-1 to G-1, the steel components were within the ranges specified in the present invention and any of the average ferrite grain sizes was not smaller than 20  $\mu\text{m}$ . The yield ratios (YRs) of the 5%-prestrain specimens were in the range from 71 to 89%. In the cases of Symbols B-1~~[[, D-1]]~~ and G-1 wherein pearlite or cementite was spheroidized, the YRs of the 5%-prestrain specimens were lower than the other specimens.